

## Mondéco Special

### Product Description

Mondéco Special is a four-component, solvent-free, epoxy-based product for terrazzo coatings.

### Uses

Mondéco Special is a product that is used for decorative floor coatings intended for use in industrial and commercial areas.

### Environment & Health

Mondéco Special is a solvent and nonylphenol free product, and practically odourless. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken.

For more information, please refer to the safety datasheets for the individual components.

### Ratio of Components

The product is supplied as A+B+C+D. Do not split the compounds/components as this may jeopardise the end result.

Add all of Hardener B to Base A. Mix with slow speed drill and helical spinner, taking care not to entrain air. Transfer to a with forced action mixer (e.g. Creteangle or Pennine) before adding Filler C and Filler D. Ensure that all Filler C and Filler D are mixed in from the sides of the container.

### Application Temperature

The recommended substrate temperature is 15-35°C, but no less than 10°C. The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening. Temperatures should not fall below 5°C in the 24 hrs after application.

### Application Time/Pot Life

Ready-mixed product should be used within 30 minutes at a temperature of 18°C. At higher temperatures the application time is shorter.

### Cure Time (20°C)

Can be walked over after 16 hours. The product must be allowed to harden for 48 hours at 20°C before grinding. If the temperature is significantly higher than 20°C, grinding may begin earlier. The product is fully hardened after 5-7 days.

### Solids Content

Approx. 100%

### Finish

Gloss

### Density

Component A approx. 1.15 kg/litre  
Component B approx. 1.04 kg/litre  
A+B+C approx. 2.65 kg/litre

**Storage**

12 months in unopened pack at a temperature of 5-40°C.  
Protect from weather and moisture/contaminant ingress.

**Packaging**

The product is delivered in the following packs.

Unit		Base A	Hardener B	Filler C	Filler D
45 kg	(16.9 litres)	7.62 kg	2.79 kg	6.45 kg	28.14 kg

Any recommendation or suggestion relating to the use of the products made by Flowcrete Middle East FZCO, whether in its technical literature, or in response to a specific enquiry, or otherwise, is based upon data believed to be reliable, however the products and information are intended for use by Customers having requisite skill and know-how in the industry and therefore it is for the Customer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the Customer has done so at its sole discretion and risk.