

Peran STB Compact (3 mm)

A hard wearing, decorative resin floor with natural quartz granules in a clear resin binder.



Attractive:

Decorative floor finish that delivers the wow-factor underfoot.



Wear Resistant:

Excellent general wear, tear, impact and chemical resistance underfoot.



Easy-to-Clean:

Seamless, hygienic finish that is easy to clean and maintain.

Commercial











Biscuit 102

Black 901











Grass Green

Light Grey 701 Mid Blue 501 Mid Grey 702

Industrial









Blue 502



Grey 704

Cream 103

Green 602



Red 301


Yellow 104

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

08 EN 13813

Technical Profile* FIRE RESISTANCE EN 13501-1 B_{fl} -s1 **WEAR RESISTANCE** EN 13892-5 Abrasion quantity 1 cm³ TEMPERATURE RESISTANCE Tolerant up to 70°C (intermittent) or 50°C (sustained) IMPACT RESISTANCE EN ISO 6272 15 Nm BOND STRENGTH EN 13892-8 >2.5 N/mm² WATER PERMEABILITY Karsten Test Nil (Impermeable) VAPOUR PERMEABILITY ASTM E96:90 $1.36 g / m^2 / mm / 24 hrs$ SLIP RESISTANCE** BS 7976-2 (typical values Dry >40 low slip potential for 4-S rubber slider) **COMPRESSIVE STRENGTH** EN 13892-2 >40 N/mm² **FLEXURAL STRENGTH** EN 13892-2 15 N/mm² TENSILE STRENGTH BS 6319-7 10 N/mm² BS 8204-6 / FeRFA Type 4 **SPEED OF CURE** 10°C 20°C $30^{\circ}C$ Light Traffic 36 hrs 24 hrs 16 hrs **Full Traffic** 48 hrs 48 hrs 72 hrs Full Chemical Cure 12 days 7 days *These figures are typical properties achieved in laboratory tests at $20\,^\circ\text{C}$ and at 50% Relative Humidity.

**The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/ or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirement for wet conditions and/ or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.



any other information please contact your local Flowcrete Technical Department

Model Specification

System	Peran STB Compact
Finish	Matte

Preparatory work and application in accordance with manufacturer's instructions.

Products Included In This System

Primer	Peran STC @ 0.25 kg/m²
Scatter	Natural Quartz size 5F (1.0–1.8 mm) @ 0.5 kg/m ²
Bodycoat	Peran STC @ 1.0 kg/m² mixed with: Compact White (STC Filler) @ 1.0 kg/m²
Scatter	Coloured Quartz Size 0.3-0.8mm @ 3.5 kg/m² (full blind)
Sealer	Peran STC @ 0.2 kg/m² and Flowseal UV Clear Matt @ 0.1 kg/m²

Detailed application instructions are available upon request.

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Peran STB system.

Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme.

Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk

Aftercare

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Stoncor Middle East LLC constitute potential options only and do not constitute nor replace professional advice in such regard. Stoncor Middle East LLC recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Stoncor Middle East LLC. Please consult Technical Team in your own country region for specific details. [11/12/18, 01]

UAE Office: StonCor Middle East LLC I PO Box 3034 Dubai United Arab Emirates I Tel: +971 4 347 0460 Email: uae@flowcrete.com

Flowcrete in the Middle East is manufactured and sold by StonCor Middle East LLC under license from Flowcrete UK.